

PRODUCT INFORMATION LEWABRANE® RO B085 HF 4040




The Lewabrane® RO B085 HF 4040 elements are spiral wound, composite polyamide membrane elements designed for industrial water treatment applications, such as the treatment of brackish and low salinity waters for primary demineralization in boiler water and process water applications.

General Information

	Metric Units	US Units
Feed spacer thickness	0.8 mm	31 mil
Membrane area	7.9 m ²	85 ft ²
Salt rejection, av.	99.5 %	99.5 %
Salt rejection, min.	99.0 %	99.0 %
Permeate flow rate, av.	8.9 m ³ /d	2400 gpd
Permeate flow rate, min.	7.1 m ³ /d	1900 gpd

Element is tested under the following conditions: applied pressure 15.5 bar (225 psi), NaCl concentration 2000 mg/l, operating temperature 25 °C (77 °F), pH 7 and recovery rate 15 %.

Element Dimension



	A (Length)	B (Diameter)	C (OD)	D (Length)
Metric Units	1016 mm	100 mm	19 mm	26 mm
US Units	40 inch	4.0 inch	0.75 inch	1.05 inch

This document contains important information and must be read in its entirety.

Edition: 2013-09-18
Previous Edition: Not available

Application Data

	Metric units	US units
Operating pressure, max.	41 bar	600 psi
Operating temperature, max.	45 °C	113 °F
Feed water SDI, max.	5	5
Feed flow, max.	4.0 m ³ /h	18 gpm
Concentrate flow, min.	0.6 m ³ /h	3 gpm
pH range during operating	2 - 11	2 - 11
pH range during cleaning	1 - 12	1 - 12
Pressure drop per element, max.	1.0 bar	15 psi
Pressure drop per vessel, max.	3.5 bar	50 psi
Chlorine concentration, max.	0.1 ppm	0.1 ppm

Additional Information

- Treat RO Elements with care; do not drop the element.
- Each RO Element is wet tested, preserved in a 1% weight sodium bisulfite solution, and vacuum packed in oxygen barrier bags.
- During storage, avoid freezing and direct sunlight. The temperature should be below 35 °C (95 °F).

After Installation

- Keep the RO Elements wet, and use a compatible preservative for storage duration longer than 7 days.
- During the initial start up, discharge the first permeate to drain for 30 min.
- Permeate back pressure should not exceed feed pressure at any time.
- Consider cleaning, if the pressure drop increases by 20% or water permeability decreases by 10%.
- Use only chemicals which are compatible with the membrane.
- For additional information consult the Lewabrane® technical information available at www.lewabrane.com.

This information and our technical advice – whether verbal, in writing or by way of trials – are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. Our advice does not release you from the obligation to check its validity and to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with the current version of our General Conditions of Sale and Delivery.

LANXESS Deutschland GmbH
BU LPT
D-50569 Köln

www.lewabrane.com
www.lanxess.com